1. A multilayer composite comprising a facestock having bottom and top surfaces, at least the bottom surface of said facestock being printable, and a carrier sheet laminated directly to the top surface of said facestock at an interface therebetween.

2. The composite of claim 1 wherein said facestock comprises a film selected from the group consisting of vinyl, urethane, acrylic, polyester, polypropylene, polyethylene, and blends thereof.

3. The composite of claim 1 wherein said facestock distorts more than 1.0% in either the machine or cross machine directions when in an unrestrained state and exposed to temperatures above about 140°F.

4. The composite of claims 1 or 3 wherein said facestock distorts more than 1.0% in either the machine or cross machine directions when subjected to tension greater than about 0.5 PLI.

5. The composite of claims 1, 2, 3 or 4 wherein said facestock has low flexural stiffness.

6. The composite of claim 1 wherein the thickness of said facestock is between about 0.25 to 3.5 mils.

7. The composite of claim 6 wherein said thickness is between about 1 and 3 mils.

8. The composite of claim 1 wherein said facestock has elongation characteristics as measured in accordance with ASTM D-822 greater than 50% in at least one direction.

9. The composite of claim 8 wherein said elongation characteristics are greater than 100% in at least one direction.

10. The composite of claim 1 having a stiffness greater than about 60 grams.

11. The composite of claim 1 wherein the bond strength at said interface is less than the respective tensile strengths of said facestock and said carrier sheet.

12. The composite of claim 1 wherein the bond strength at said interface is less than the yield strength of said facestock.

13. The composite of claim 1 wherein the bond strength at said interface as measured in accordance with FTM3 is less than 200 grams per 2 inch width.

14. The composite of claim 13 wherein said bond strength is less than 100 grams per 2 inch width.

15. The composite of claim 14 wherein said bond strength is less than 60 grams per 2 inch width.

16. The composite of claim 3 wherein the stiffness and tensile strength of said carrier sheet is such as to prevent said distortion.

17. The composite of claim 1 further comprising a liner releasably adhered by means of a pressure sensitive adhesive to the bottom surface of said facestock.

18. The composite of claim 17 further comprising graphics interposed between the bottom surface of said facestock and said pressure sensitive adhesive.

19. The composite of claim 18 wherein said graphics are printed on the bottom surface of said facestock.

19. The composite of claim 1 wherein said carrier sheet comprises a film selected from the group consisting of polyester, polypropylene and polystyrene and surface modifications thereof.

20. The composite of claim 1 wherein said carrier sheet is selected from the group consisting of extrusion coated paper and extrusion coated film.